



SPEC-ONE 8000 Exterior Lo-Lustre (8301-8304)

SPEC-ONE 8000 Exterior Lo-Lustre provides tenacious adhesion to a variety of substrates. It is mildew and blister resistant, exhibits excellent durability and superb color retention. It is an excellent choice for painting pre-finished siding.

Recommended Substrates: Wood, Metal, Masonry, Aluminum

Application: Stir product thoroughly with a circular, lifting motion ensuring even mixing throughout. SPEC-ONE 8000 may be applied by brush, spray, pad or roller at a rate of application not to exceed 450 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" or 1/2" nap cover for smooth surfaces, a 3/4" nap cover for semi-rough surfaces and a 1" or 1 1/2" nap cover for rough surfaces. For spray application, product may be thinned with clean water, up to 20% reduction, if necessary. Apply only when surface and air temperatures are between 50 and 90 degrees Fahrenheit. Do not apply if rain is threatening. May be applied with airless spray equipment. Tip sizes and atomization pressures will vary with the type of equipment used. Usually an 8 to 12 inch fan at one foot distance is ideal for airless and can be obtained with a tip size from .015 to .019 inches. Follow spray equipment manufacturers recommendations. Do not apply at more than recommended spread rate given on product label.

Product Type: 100% Acrylic
Volume Solids: 38.3 ± 1.0%
Weight Solids: 52.5 ± 1.0%
Weight Per Gallon: 10.8 lbs.
Viscosity: 95 to 100 KU (Krebs Units)
Flash Point: 200°F. or greater (TT-P-141, Method 4293)
Specular Gloss: 32 to 37 units @ 85 Degrees
Wet Film Thickness: 3.6 to 4.6 mils
Dry Film Thickness: 1.4 to 1.8 mils
VOC: max of 100 g/L (0.83 lbs/gal)

Dry Time: to touch = 30 mins; recoat = 4 hours; full cure = 7 to 10 days.

Thinner: Clean water.

Clean Up: Warm, soapy water.

Disposal: Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations. Do not pour down a drain or storm sewer.

The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with TSP (or equivalent) and water, followed by a clean water rinse. Mildew must be removed by washing the surface with a solution of one part household bleach mixed with three parts water. Rinse well with clean water following wash. Wax should be removed by solvent cleaning. Grease and oil should be cleaned by using an appropriate emulsifier. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. It is not necessary to dull contamination. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. **Priming:** product is self-priming on non-bleeding woods such as Southern Yellow Pine and Ponderosa Pine; however, spot prime all knots and nail heads with an appropriate stain-blocking primer. Redwood, Cedar or other bleeding type woods should be primed with an appropriate primer. SPEC-ONE 8000 Lo-Lustre is self-priming when used on Galvanized Metal, Aluminum Siding and Masonry. Use an appropriate primer on Ferrous Metal.

Warning: Use only with adequate ventilation. Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Contains Ethylene Glycol & Crystalline Silica. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately. If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations. Obtain and read the MSDS prior to using this product. **KEEP OUT OF REACH OF CHILDREN.**