



**Spectrum Paint Spec-Pro®**  
**Buildermax® Supreme**  
 Interior Flat Latex  
 35101

## GENERAL DESCRIPTION

SPEC-PRO® Buildermax® Supreme Interior flat latex is designed as a high-hiding, easy-to-apply interior wall paint that delivers exceptional touch-up to get the job done on time and within budget. Low VOC and low-odor, this paint is recommended for all commercial, maintenance, and residential applications where an ultra flat, uniform finish is desirable.

## RECOMMENDED SUBSTRATES

Concrete/Masonry	Gypsum Wallboard-Drywall
Concrete Block (CMU)	Plaster
Ferrous Metal	Wood

## CONFORMANCE STANDARDS

VOC compliant in all regulated areas

## LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors.

PROTECT FROM FREEZING.

## PRECAUTIONS

**WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED.** Do not breathe vapor or mist. Do not swallow. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. Note: These warnings encompass the product. Prior to use, read and follow product-specific SDS and label information. **FIRST AID:** if swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Keep out of the reach of children. For SDS, call 412-492-5555. EMERGENCY SPILL INFO: 412-434-4515 (U.S.).

## FEATURES / BENEFITS

### Features

- Less than 50 g/L VOC
- Exceptional Airless Spray Touch-Up
- Good Hiding Power
- Good Burnish Resistance

### Benefits

- Meets the most stringent VOC regulations nationwide
- Reduces labor costs
- Hides surface imperfections
- Resists sheen change when cleaned

## APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. **USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.** Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high-quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

**Airless Spray:** Pressure 1500 to 2000 psi; tip 0.015" to 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Polyester/Nylon Brush

**Roller (nap roller cover):** 3/8" - 3/4"

**Thinning:** Do not thin.

Read Label and Safety Data Sheet prior to use.

## PRODUCT DATA

<b>PRODUCT TYPE:</b>	Vinyl Acrylic Latex
<b>SHEEN:</b>	Flat, 1-3 @85°
<b>VOLUME SOLIDS*:</b>	34% +/- 2%
<b>WEIGHT SOLIDS*:</b>	54% +/- 2%
<b>WEIGHT/GALLON*:</b>	11.9 lbs. (5.4 kg) +/- 0.2 lbs. (91 g)
<b>VOC:</b>	<50 g/L (0.4 lbs./gal.)

**COVERAGE:** Approximately 300 to 400 sq. ft. (28 to 37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 to 5.3 mils
Wet Microns:	102 to 135
Dry Film Thickness:	1.4 to 1.8 mils
Dry Microns:	36 to 46

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing. Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

<b>DRYING TIME:</b>	Dry time @ 77°F (25°C); 50% relative humidity.
To Touch:	30-60 minutes
To Recoat:	2-4 hours
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. Wait at least 30 days after painting before cleaning the surface with a non-abrasive, mild cleanser. Very deep colors may require longer to fully cure.

**CLEANUP:** Clean tools with warm, soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

**FLASH POINT:** Over 200°F (93°C)