



SPEC-PRO White Pigmented Sealer

DESCRIPTION		
<p>This high solids white lacquer sealer produces a film with rapid dry characteristics and excellent sandability. This product builds quickly and provides exceptional hide. For wood substrates only. For interior use only.</p>		
PRODUCT NUMBERS / SHEENS	COATING PROPERTIES	PREPARATION INSTRUCTIONS
12000	<p>Viscosity: 96K.U. Weight Solids: 42.61 % Volume Solids: 24.55 % Weight/Gallon: 9.29 lbs./gal Coverage: 393 sq. ft. per gallon at one mil dry film thickness.</p> <p>VOC (coating): 5.32 lbs./gl. or 638 g/l VOC (material): 5.31 lbs./gl. or 636 g/l VOC Ratio: 1.34 lbs. VOC/lbs. Solids HAPS Ratio: 1.08 lbs. HAPS/lbs. Solids</p> <p>Dry Times: Air Dry: at 78°F, relative humidity 50% To touch: 4 minutes To handle: 4 minutes To sand/recoat: 20 minutes</p> <p>Relative humidity will affect the speed of drying. Ideal conditions are 75° F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower humidity and equally slower at colder temperatures and higher humidity.</p> <p>Dry Film Thickness: For best results, the DFT for this primer should be between .75-1.5 mils. Please refer to the PDS for the specific topcoat you are using for maximum DFT for the complete system.</p> <p>Shelf Life: 12 months @77° F if unopened and stored in a cool dry area. Always rotate stock.</p> <p>Storage: Keep away from heat or sparks.</p>	<p>Reduction: Thinning: This product is supplied ready to spray for airless application. If needed due to conditions in your facility use lacquer thinner at levels not to exceed 30% by volume*</p> <p>Retarder: Retarders should not be used in a primer or sealer as they may affect the dry and cure of the topcoat.</p> <p>*Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning.</p> <p>Approved Companion Products 11500 Semi Gloss White Lacquer 11300 Satin White Lacquer</p> <p style="font-size: 0.8em; margin-top: 20px;"><i>Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</i></p>
PRODUCT ADVANTAGES		
<ul style="list-style-type: none"> ➤ AIM Compliant ➤ High Solids ➤ High Build ➤ Fast Dry ➤ Excellent Sandability ➤ Phthalate Free 		

Revised July 8, 2016

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, SPECTRUM PAINT MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL SPECTRUM PAINT BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF SPECTRUM PAINT FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY SPECTRUM PAINT SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. **CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE** using this product it is essential that the "Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

PRODUCT DATA SHEET SPEC-PRO WHITE SEALER CONTINUED



Substrate preparation:

New wood: Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.



Mixing Instructions:

Mix material thoroughly before and during use. Material may be mixed by hand or mechanical agitation at moderate speed.



Application:

Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum 20 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air, or tack rag.

Typically we recommend a coating system comprised of one coat of 12000 applied at 3-4 mils wet film build and 1-2 coats of an approved topcoat. Refer to the Product Data Sheet for the topcoat you are using for maximum dry film thickness recommendations.



Recommended Tip Sizes:

Conventional Air	1.3-1.8mm
HVLP	1.3-1.8mm
Airless	10-15 thousandths
Air Assisted Airless-	11-15 thousandths



Precautions:

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Spectrum Paint will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations

Equipment:

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts

Containers:

We supply this material in a lined container. All containers used in conjunction with storage and/or application of this product must be stainless steel, plastic, or otherwise acid resistant.

Clean up:

Use lacquer thinner to clean up all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

Care and cleaning of this finish: Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.