



Technical Data Sheet

Product Name

Spectrum Admiral Pre-Catalyzed Clear Lacquer

Product Codes: 17110 (Flat), 17210 (Dull Rubbed), 17310 (Satin), 17510 (Semi-Gloss), 17910 (Gloss)

Product Description

Admiral Professional Pre-Catalyzed Lacquers are designed to offer a fast drying, durable, easy to apply, premium finish. For Professional use only. Wood Substrates only. A combination sanding sealer/ finish coat that dries to a smooth, clear finish. Available in flat, dull-rubbed, satin, semi-gloss, or gloss finish.

Features

- Ready to spray as supplied.
- Provides a tough, flexible finish
- Can be used as a self-sealing system of over Spectrum Admiral 17010 or 16010 Sanding Sealer

Technical Data

Viscosity: 26-30 seconds #2 Signature Zahn (Flat/Dull Rubbed); 26-34 seconds (Satin, Semi-Gloss, Gloss)
Sheen Levels: 8-12 (Flat), 16-22 (Dull Rubbed), 38-42 (Satin), 55-60 (Semi-Gloss), 80-99 (Gloss)
Density: 7.67-7.93 lbs./gallon
% Solids by weight: 26.00-30.00%
Dry to sand & recoat: 30-45 minutes

Surface Prep

Surface area must be clean and dust free with a moisture content not to exceed more than 8% prior to application. Proper sanding, and keeping the application area free of dust, are instrumental to achieve the best results.

Application Guidelines

All products should be stirred before use and continually agitated while in use for best results. This product can be applied by airless or air assisted spray. All surfaces must be clean and dry. Sand bare wood with 150 grit sandpaper. Apply 3-4 wet mils per coat. Do not exceed 5 mils DFT. Scuff/Sand between coats with 220-320 grit sandpaper, allowing 30-45 minutes to dry between coats. After sanding, wipe away all sanding dust before applying subsequent coats. For interior use only.

Disclaimer

Spectrum Paint Co. certifies the above product meets the agreed upon performance specifications. Spectrum Paint Co. is not responsible for the misuse and subsequent product failure. No warranty is expressed or implied in such instances. All products utilized in conjunction with 17110, 17210, 17310, 17510, or 17910 need to be tested in advance to ensure compatibility. User assumes all risk with such endeavors. Consult the SDS for specific hazards. For technical support, please contact your local Spectrum Paint account manager or store.