



## 28000 Admiral Quick Dry Alkyd Wiping Stain-Clear Base

28000 is a clear wiping stain base for tinting custom colors. Designed for the professional wood finisher, these stains will provide rich, deep colors, in a product that is incredibly easy to apply and offers a quick recoat time. These stains are designed for application to interior wood substrates only.

Recommended uses include: Kitchen cabinetry, bathroom cabinetry, interior woodwork, and architectural millwork.

This stain may be applied by spray, brush, or cloth rag. When spraying set the air pressure as low as possible, typically 12 - 15 psi. If the pressure is set too high, it may cause the stain to dry prematurely. Apply an even, wet coat. Leave the stain for 30-45 seconds. While the stain is still wet remove the excess with a clean, lint free cloth by working the stain into the wood with a circular motion, and finish by wiping with the grain. Let dry a minimum of 30-45 minutes.

Product Type: Alkyd Wiping Stain Clear Base

Viscosity: N/A Weight Solids: 38% Volume Solids: 34%

VOC (reg./coating): 4.6 lbs./gl. or 546 g/l VOC (act/material): 4.6 lbs./gl. or 546 g/l VOC Ratio: 1.62 lbs. VOC/lbs. Solids HAPS Ratio: 0.08 lbs. HAPS/lbs. Solids

Dry Time to recoat at 77°F & < 50% RH: 30-45 minutes

Shelf Life: 24 months @77° F if unopened and stored in a cool

dry area. Always rotate stock.

Coverage: 538 sq. ft. per gallon at one mil dry film thickness. Clean Up: Use lacquer thinner or acetone to clean up all

equipment.

Disposal: Dispose of in accordance with Federal, State, and

Local regulation regarding pollution Storage: Keep away from heat or Sparks

## **Substrate Preparation:**

**New wood:** Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%. Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

**Old wood**: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.

*Note:* This Technical Data Sheet is accurate to the best of our knowledge. However, as application conditions and intended end use are beyond our control, no warranty as to fitness or merchantability is expressed or implied. Customers are urged to confirm their own results.

January, 2024